



SPEEDHIDE®

6-208, 6-212

Architectural Coatings

GENERAL DESCRIPTION

Recommended for properly prepared iron and steel surfaces for either interior or exterior service. SPEEDHIDE® Rust Inhibitive Primer provides surface corrosion protection under normal exposure conditions. **FOR METAL SUBSTRATES ONLY.**

RECOMMENDED SUBSTRATES

Ferrous Metal

FEATURES / BENEFITS

Excellent Adhesion

Corrosion-Resistant in Normal Atmospheric Conditions

Performance Offset to Federal Standards TT-P-636, TT-P-0645, TT-P-0664

6-212, MPI category #23, Surface Tolerant Metal Primer and MPI category #79, Primer, Alkyd, Anti-Corrosive for Metal

DIRECTIONS FOR USE

Stir thoroughly before using and frequently during use. When using more than one can of the same color, mix together (box) before applying. **USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN.** Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

Permissible temperatures during application:

Material: 60 to 90°F 16 to 32°C

Ambient: 50 to 100°F 10 to 38°C

Substrate: 50 to 130°F 10 to 54°C

APPLICATION INFORMATION

Application Equipment: Apply with a high quality brush, roller, paint pad, or by airless spray equipment. Where necessary, apply a second coat.

Conventional Spray: Graco 210-961 Series A or equivalent. 0.070" (1.78 mm) cap, 0.061" (1.55 mm).

Airless Spray: Pressure 2000 psi - 2600, tip 0.015" - 0.023" Hose diameter: 1/4" maximum length 50 feet, rise from pump 20-50 feet.

Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury. Explosion-proof equipment must be used when coating with these materials in confined areas. Keep containers closed and away from heat, sparks, and flames when not in use.

Brush: High quality Polyester/Nylon brush

Roller: High quality nap roller cover

Thinning: DO NOT THIN.

SPEEDHIDE® Interior/Exterior Rust Inhibitive Steel Primers

TINTING AND BASE INFORMATION

6-208	Red
6-212	White

DO NOT TINT.

PRODUCT DATA

PRODUCT TYPE:	Alkyd Resin
VOLUME SOLIDS*:	57% +/- 2%
WEIGHT SOLIDS*:	76% +/- 2%
VOC*:	330 g/L (2.75 lbs./gal.)
WEIGHT/GALLON*:	11.0 lbs. (5.0 kg) +/- 0.2 lbs. (91 g)

*Product data calculated on product 6-212.

COVERAGE: Approximately 400 sq. ft./gal. (37 sq. m/3.78L) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness:	4.0 mils
Wet Microns:	101.6
Dry Film Thickness:	2.3 mils
Dry Microns:	58.4

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

DRYING TIME: Dry time @77°F (25°C); 50% relative humidity.

To Touch:	8 hours
To Handle:	16 hours
To Recoat:	16 hours

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

If left untopcoated for longer than 7 days, cleaning and light sanding of the surface is recommended. Allow to dry 24 hours before applying water base topcoat.

CLEANUP: Paint Thinner

DANGER: Rags, steel wool or waste soaked with this product may spontaneously catch fire if improperly discarded. Immediately after use, place rags, steel wool or waste in a sealed water-filled metal container. Refer to www.pittsburghpaints.com, Spontaneous Combustion Advisory for additional information.

FLASH POINT: 106°F (41.1°C)

GENERAL SURFACE PREPARATION

The surface to be coated must be dimensionally stable, dry, clean, and free of oil, grease, release agents, curing compounds, and other foreign materials. The service life of the coating is directly related to the surface preparation. Surface must be clean, dry and free from dirt, loose paint, oil, grease, wax, rust, loose mill scale and other contamination. Remove oil and grease by solvent cleaning. Sand all slick or glossy surfaces. Minimum surface preparation: SSPC-SP-2, Hand Tool Cleaning. Recommended surface preparation: SSPC-SP 6 Commercial Blast. Anchor pattern requirement 1.0 to 1.5 mils suitable for a thin film alkyd system. For most direct-to-metal applications, brushing may improve adhesion to the surface. Primer should not be left untopcoated for an extended period of time. Finish coats should be applied as soon as possible after primer has dried. If the primer is left untopcoated for longer than 7 days, cleaning and light sanding of the surface is recommended. On exterior surfaces, remove and inhibit regrowth of mildew by using PPG MILDEW CHECK® Multi-Purpose Wash, 18-1. Before use, be sure to read and follow the instructions and warnings on the PPG MILDEW CHECK® Multi-Purpose Wash label.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

FERROUS METAL: The recommended surface preparation is Commercial Blast Clean per SSPC-SP6. The minimum surface preparation is Hand Tool or Power Tool Clean per SSPC-SP2 or SP3.

LIMITATIONS OF USE

Apply when air and surface temperatures are above 50°F (10°C) and surface temperature is at least 5°F (3°C) above the dew point. Avoid exterior application late in the day when dew and condensation are likely to form or if rain is expected. Not intended for use as a finish coat or for immersion service.

Not recommended for use on floors.

PACKAGING

1-Gallon (3.78 L)
5-Gallon (18.9 L)

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.pittsburghpaints.com

Technical Services
1-800-441-9695
1-888-807-5123 fax

Architect/Specifier:
1-888-PPG-IDEA

PPG Architectural Finishes, Inc.
400 S. 13th Street
Louisville, KY 40203

PPG Canada, Inc.
Architectural Coatings
4 Kenview Blvd
Brampton, ON L6T 5E4

D3 8/2010
(Supersedes 4/2008)