



## Architectural Coatings

## SPEEDHIDE zero Interior Zero-VOC\*\* Latex Sealer

## GENERAL DESCRIPTION

PPG *SPEEDHIDE* zero Interior Latex Sealer is a professional grade zero-VOC\*\* interior acrylic primer formulated to meet the performance requirements of professional applicators. *SPEEDHIDE* zero Interior Latex Sealer can be used as a primer under alkyd or latex finish coats and is ideal under a variety of finishes. This zero-VOC\*\*, low-odor paint is ideal for painting occupied spaces while delivering the durable product performance required. It provides excellent sealing properties. Recommended for use on properly prepared interior wallboard and drywall surfaces, wood, and oriented strand board or particle board, and masonry.

## RECOMMENDED SUBSTRATES

Gypsum Wallboard-Drywall    Particle Board    Wood  
Oriented Strand Board    Masonry

## CONFORMANCE STANDARDS

- ✓ VOC compliant in all regulated areas
- ✓ Can earn LEED® 3.0 credits
- ✓ Meets GREENGUARD® Indoor Air Quality and GREENGUARD Children & Schools
- ✓ Meets the Collaborative for High Performance Schools (CHPS) Low-Emitting Materials criteria section 01350
- ✓ MPI® approval in category #50, Primer Sealer, Latex Interior
- ✓ MPI approval in category #149, Latex Interior Institutional Low Odor/VOC Flat (MPI Gloss Level 1)
- ✓ Meets MPI Green Performance Standards (GPS-1 and GPS-2)
- ✓ MPI approval in category #50 X-Green
- ✓ MPI approval in category #149 X-Green

## APPLICATION INFORMATION

Stir thoroughly. When using more than one container of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

**Application Equipment:** Apply with a high quality brush, roller, paint pad, or by airless spray equipment. Where necessary, apply a second coat.

**Airless Spray:** Pressure 2000 psi, tip 0.015" - 0.021"

Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

## FEATURES / BENEFITS

## Features

0 g/L VOC\*\*  
Low odor  
Fast drying  
Great adhesion  
Excellent sealing properties  
Great enamel holdout  
Soap and water clean-up  
MPI approved  
Can earn LEED 3.0 credits

## Benefits

Meets the most stringent environmental regulations nationwide  
Ideal for painting in occupied spaces  
Same day topcoat turning jobs faster  
Improves durability of finish  
Provides a uniform finish  
Promotes even sheen in topcoats  
Safe waterborne formula  
Meets strict performance and aesthetic requirements  
Contributes to sustainable design

## APPLICATION INFORMATION (continued)

**Brush:** Polyester/Nylon Brush

**Roller:** 3/8" - 3/4" nap roller cover

**Thinning:** Thinning is not usually required. If necessary, thin with up to 1/4 pint (118mL) of water per U.S. gallon (3.78 L) of paint.

**Permissible temperatures during application:**

Material:	50 to 90°F	10 to 32°C
Ambient:	50 to 90°F	10 to 32°C
Substrate:	50 to 90°F	10 to 32°C

## PRODUCT DATA

**PRODUCT TYPE:** 100% Acrylic Latex

**SHEEN:** Flat

**VOLUME SOLIDS:** 35% +/- 2%

**WEIGHT SOLIDS:** 50% +/- 2%

**VOC\*\*:** 0 g/L (0 lbs./gal.)

**WEIGHT/GALLON:** 10.8 lbs. (4.9 kg) +/- 0.2 lbs. (91 g)

**COVERAGE:** Approximately 400 sq. ft./gal. (37 sq. m/3.78L) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness: 4.0 mils

Wet Microns: 102

Dry Film Thickness: 1.4 mils

Dry Microns: 36

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

**DRYING TIME:** Dry time @ 77°F (25°C); 50% relative humidity.

To Touch: 30 minutes

To Recoat: 4 hours

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

**CLEANUP:** Clean tools with warm soapy water.

**DISPOSAL:** Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

**FLASH POINT:** Over 200°F (93°C)

\*\*Colorants added to this base paint may increase VOC level significantly depending on color choice.

## GENERAL SURFACE PREPARATION

Surfaces to be coated must be dry, clean, sound, and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, concrete curing agents and bond breakers, chalk, efflorescence, mildew, rust, product fines, and dust. Remove loose paint, chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Feather back all rough edges to sound surface by sanding.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead). In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

**GYPSUM WALLBOARD-DRYWALL:** Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust before priming the substrate.

**MASONRY:** New masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming with an alkali resistant primer.

**ORIENTED STRAND BOARD:** Countersink all nails or screws and putty flush with the surface. Surface should be cleaned to remove any dust or contaminants before priming the substrate.

**PARTICLE BOARD:** Countersink all nails or screws and putty flush with the surface. Surface should be cleaned to remove any dust or contaminants before priming the substrate. (Veneered surfaces should be sanded smooth and cleaned to remove any dust or contaminants, before priming the substrate.)

**WOOD:** Unpainted wood or wood in poor condition should be sanded smooth and wiped clean before priming the substrate. Spot prime knots or resinous areas before the application of the first full coat of primer. Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust before priming the substrate.

## LIMITATIONS OF USE

FOR INTERIOR USE ONLY.

Apply when air, surface and product temperatures are between 50°F (10°C) and 90°F (32°C).

Not recommended for use on floors.

PROTECT FROM FREEZING.

## TINTING AND BASE INFORMATION

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

6-4900XI

White

Some colors, drastic color changes, or porous surfaces may require more than one coat to achieve a uniform finish.

## PACKAGING

1-Gallon (3.78 L)

5-Gallon (18.9 L)

The PPG logo is a registered trademark and *Ecological Solutions from PPG* is a trademark of PPG Industries Ohio, Inc. *SPEEDHIDE* is a registered trademark of PPG Architectural Finishes, Inc. The *GREENGUARD* Indoor Air Quality Certified Mark is a registered trademark used under license through the *GREENGUARD* Environmental Institute. *LEED* is a registered trademark of the US Green Building Council. The *Master Painters Institute* and *MPI* are registered trademarks of Master Painters Institute, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.  
Architectural Coatings  
One PPG Place  
Pittsburgh, PA 15272  
[www.ppgpittsburghpaints.com](http://www.ppgpittsburghpaints.com)  
[www.ppgporterpaints.com](http://www.ppgporterpaints.com)

Technical Services  
1-800-441-9695  
1-888-807-5123 fax

Architect/Specifier  
1-888-PPG-IDEA

PPG Canada, Inc.  
Architectural Coatings  
4 Kenview Blvd  
Brampton, ON L6T 5E4

A1.47 3/2013  
(Supersedes 1/2013)

Made in the  
**USA**