

HPC/Industrial Maintenance

GENERAL DESCRIPTION

Pitt-Tech Plus Satin Industrial Enamels are a full line of 100% Acrylic waterborne enamels designed for direct-to-metal application. These products provide corrosion protection, chemical and solvent resistance, and are fast drying with low odor. Recommended for use on properly prepared interior or exterior metal, masonry, plaster, and drywall surfaces. **For Professional Use Only; Not Intended for Household Use.**

RECOMMENDED USES

Aluminum	Concrete, Stucco, Plaster, Masonry
Drywall	CMU
Ferrous Metal	Galvanized Steel
	Wood

FEATURES AND BENEFITS

Excellent adhesion for true DTM performance
Improved color, and gloss retention versus most alkyds, water-base and two-component systems.
High hiding
Flash rust resistant
Easy to apply, low odor
Performance Offset to Federal Standard TT-E-2784 and MIL-P-28578
Meets MPI® Category #151, Light Industrial Coating, Interior W.B. Semi Gloss,
Meets MPI Category #161, Light Industrial Coating Exterior W.B., Gloss, MPI Gloss Level 3
Can help earn LEED® 2009 credits

MIXING AND APPLICATIONS INFORMATION

Mix thoroughly before and during use.

Permissible temperatures during application:

Material:	50° to 90° F	10°C to 32°C
Ambient:	40° to 100° F	4°C to 38°C
Substrate:	40° to 120° F	4°C to 49°C

Application Equipment: Changes in application equipment, pressures and/or tip sizes may be required depending on ambient temperatures and application conditions.

Brush: High Quality Polyester/Nylon Brush

Roller: 3/8" nap roller cover

Airless Spray: Pressure 1800 - 3150 psi, tip 0.013" to 0.019"

Graco Ultra Max Series pumps with contractor guns or equivalent.

Conventional Spray: Fluid Nozzle: DeVilbiss 510 gun, with 704 or 777 air cap with E tip and needle, or comparable equipment. Atomization Pressure: 55-70

Fluid Pressure: Can not specify, dependent on numerous factors.

Thinning: May be reduced up to 5% by volume with water for spray application. Thinning is not usually required for brush and roll. Excessive thinning or insufficient film thickness may cause rust staining. If rust staining occurs, apply an additional coat. Do not add oils, paint thinners, or any paint additives.

Pitt-Tech Plus Int./Ext. Satin DTM Industrial Enamel

TINTING AND BASE INFORMATION

Can be tinted with both 896 and 96 line colorants.

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

90-1110	White & Pastel Base
90-1120	Midtone Base*
90-1130	Deeptone Base*
90-1140	Deep Rustic Base*

*Must be tinted before use.

PRODUCT DATA

PRODUCT TYPE: 100% Acrylic Formula
GLOSS: Satin: 15 to 25 (Gloss 60° Meter)

VOC*: 85 g/L (0.70 lbs./gal.)

COVERAGE: 164 to 327 sq. ft./gal.
(15 to 30 sq. m/3.78L)

Note: Does not include loss due to varying application method, surface porosity, or mixing.

DFT: 2.0 to 4.0 mils

WEIGHT/GALLON*: 10.6 lbs.(4.81 kg)+/-0.2 lbs. (91g)

VOLUME SOLIDS*: 42.4% +/- 2%

WEIGHT SOLIDS*: 54.8% +/- 2%

MIXED RATIO: One Component

*Product data calculated on 90-1110.

Wet Film Thickness: 4.7 to 9.4 mils

Wet Microns: 119 to 239

Dry Film Thickness: 2.0 to 4.0 mils

Dry Microns: 50.8 to 101.6

IN SERVICE TEMP.: Dry Heat 250°F (121°C)

DRYING TIME: Dry time @77°F (25°C); 50% relative humidity.

To Touch: 15 minutes

To Handle: 30 minutes

To Recoat: 1 hour

Drying times listed may vary depending on temperature, humidity, color and air movement.

CLEANUP: Soap and Water

FLASH POINT: Over 200°F (93°C)

PACKAGING

1-Gallon (3.78L)

5-Gallon (18.9L)

GENERAL SURFACE PREPARATION

The surface to be coated must be dimensionally stable, dry, clean, and free of oil, grease, release agents, curing compounds, and other foreign materials. The service life of the coating is directly related to the surface preparation. Where appropriate bare areas should be primed with a suitable primer. For best performance for colors using midtone, deeptone or rustic bases over bare metal substrates, the use of a primer or two coats of the topcoat is recommended. Remove and inhibit regrowth of mildew on exterior surfaces by using PPG Mildew Check® Multi-Purpose Wash, 18-1. Before use, be sure to read and follow the instructions and warnings on the label. **WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN.** PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

PREVIOUSLY PAINTED SURFACES: Old coatings should be tested for adhesion of the existing system.

FERROUS METAL: Rust and other surface contaminants must be removed as per SSPC-SP2 Hand Tool or SSPC-SP3 Power Tool. Then the surface thoroughly cleaned to remove all other contaminants as per SSPC-SP1.

GALVANIZED STEEL: Solvent Clean per SSPC-SP1 to remove grease and oils. If any oxidation (white rust) has formed, sand and remove all forms of contamination. If the galvanized has been passivated or stabilized, the surface must be abraded i.e. Brush-Off Blast Clean per SSPC-SP7 or chemically treat the surface.

ALUMINUM: Solvent Clean per SSPC-SP1 to remove grease and oils.

CONCRETE, STUCCO, PLASTER, MASONRY other than CMU: Allow all concrete, mortar, plaster, etc. to cure for thirty (30) days under normal drying conditions. Remove all dirt, dust, grime, loose mortar and all other forms of contamination. Concrete which has been treated with curing compounds or hardeners, should be thoroughly abraded.

CONCRETE MASONRY UNITS: Allow the mortar to cure for thirty (30) days under normal drying conditions. Remove all dirt, dust, grime, loose mortar and all other forms of contamination.

WOOD: Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime.

RECOMMENDED PRIMERS

Interior Wood	17-921, 17-955
Concrete, Stucco, Plaster, Masonry other than CM Unit	4-603, 4-808
Concrete Masonry Units	6-15, 16-90
Drywall	6-2, 9-900, 17-921, 12-900
Aluminum	6-204, 90-712, 90-912
Exterior Wood	6-609, 17-921
Ferrous Metal	Self priming, 6-208, 7-852, 90-712, 90-912
Galvanized Steel	Self priming, 6-209, 90-712, 90-912

For more aggressive conditions, use 97-145 series, 97-946 series or 98-46 series primers.

Tannin bleeding woods may require a specialty primer.

The PPG logo is a registered trademark of PPG Industries Ohio, Inc. *Pitt-Tech* and *Mildew Check* are registered trademarks of PPG Architectural Finishes, Inc. *LEED* is a registered trademark of the US Green Building Council. The *Master Painters Institute* and *MPI* are registered trademarks of Master Painters Institute, Inc.

LIMITATIONS OF USE

For Professional Use Only; Not Intended for Household Use.

Apply only when air, product and surface temperatures are between 40°F - 100°F (4°C - 38°C) and surface temperature is at least 5°F (3°C) above the dew point. Avoid exterior painting late in the day when dew or condensation are likely to form or if rain is threatening. Two coats are required for maximum protection and durability if used as a finish coat. Do not use for immersion service. **PROTECT FROM FREEZING.** Excessive thinning or insufficient film thickness may cause rust staining. If rust staining occurs, apply an additional coat.

SAFETY

Proper safety procedures should be followed at all times while handling this product. **USE WITH ADEQUATE VENTILATION.** **KEEP OUT OF REACH OF CHILDREN.** Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury. Read all label and Material Safety Data Sheet for important health/safety information prior to use. MSDS are available through our website www.pphpc.com or by calling 1-800-441-9695.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.pphpc.com

Technical Services
1-800-441-9695
1-888-807-5123 fax

Architect/Specifier
1-888-PPG-IDEA

PPG Canada, Inc.
Architectural Coatings
4 Kenview Blvd
Brampton, ON L6T 5E4

E6 4/2012
(Supersedes 11/2011)