



**SHERWIN
WILLIAMS**



101.83a

As of 11/23/2016. Complies with:		
OTC	Yes	LEED® 09 NC,CI,CS Yes
OTC Phase II	Yes	LEED® 09 H&S Yes
SCAQMD	Yes	LEED® v4 Emissions Yes
CARB	Yes	LEED® v4 VOC Yes
CARB SCM 2007	Yes	
MPI	Yes	

PROMAR® 200

Zero VOC Interior Latex Eg-Shel B20-2600 Series

CHARACTERISTICS	SPECIFICATIONS	SURFACE PREPARATION
ProMar 200 Zero VOC Interior Latex Eg-Shel is a durable, professional quality, interior vinyl acrylic finish for use on walls, ceilings, and trim of primed plaster, wallboard, wood, masonry, and primed metal.		WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.
Color: Most colors To optimize hide and color development, always use the recommended P-Shade primer		Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with the appropriate primer/sealer. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.
Coverage: 350 - 400 sq ft/gal @ 4 mils wet; 1.7 mils dry		Drywall 1ct. ProMar 200 Zero VOC Latex Primer 2cts. ProMar 200 Zero VOC Interior Latex
Drying Time, @ 77°F, 50% RH: Touch: 1 hour Recoat: 4 hours Drying and recoat times are temperature, humidity, and film thickness dependent		Plaster 1ct. Premium Wall & Wood Primer* 2cts. ProMar 200 Zero VOC Interior Latex
Finish: 15-20 units @ 85° 5+ units @ 60°		Wood 1ct. Premium Wall & Wood Primer* 2cts. ProMar 200 Zero VOC Interior Latex
Flash Point: N/A	* These primers contain <50 g/L VOC. Other primers may be appropriate.	Block 1ct. PrepRite Block Filler* 2cts. ProMar 200 Zero VOC Interior Latex
Tinting with CCE only:		Masonry 1ct. Loxon Concrete & Masonry Primer* 2cts. ProMar 200 Zero VOC Interior Latex
Base oz/gal	Strength	
High Ref White	0-6	100%
Extra White	0-7	125%
Deep Base	4-12	100%
Ultradeep	10-12	100%
Real Red	4-12	100%
Bright Yellow	4-12	100%
Dover White		do not tint
Vehicle Type:	Vinyl Acrylic	
Extra White B20W12651 (may vary by color)		
VOC (less exempt solvents):		
<50 g/L; 0.42 lb/gal		
As per 40 CFR 59.406 and SOR/2009-264, s.12		
Volume Solids:	42 ± 2%	
Weight Solids:	54 ± 2%	
Weight per Gallon:	10.82 lb	
Anti-microbial		Drywall Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.
This product contains agents which inhibit the growth of mold and mildew on the surface of this paint film.		Masonry, Concrete, Cement, Block All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with Loxon Concrete & Masonry Primer.



**SHERWIN
WILLIAMS.**

101.83a

PROMAR® 200
Zero VOC
Interior Latex
Eg-Shel
B20-2600 Series

<u>SURFACE PREPARATION</u>	<u>APPLICATION</u>	<u>CAUTIONS</u>
Plaster Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.	Apply at temperatures above 50°F. No reduction needed.	For interior use only Protect from freezing. Non-photochemically reactive.
Wood Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.	Brush Use a nylon/polyester brush. Roller Use a 3/8" - 3/4" nap synthetic cover. Spray—Airless Pressure 2000 psi Tip017"- .021"	Before using, carefully read CAUTIONS on label HOTW 11/23/2016 B20W12651 10 00 FRC, SP, KOR, VIET
Mildew Prior to attempting to remove mildew, it is always recommended to test any cleaner on a small, inconspicuous area prior to use. Bleach and bleaching type cleaners may damage or discolor existing paint films. Bleach alternative cleaning solutions may be advised. Mildew may be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.	APPLICATION TIPS Make sure product is completely agitated (mechanically or manually) before use. Priming and application of two coats at the recommended film thickness can help where hiding of a previous coating or application to new drywall is a factor. Using the same method of application and batch to touch up with as that originally used will help improve touch up. When original application was by spray, preconditioning of touch up paint by running it through the spray tip will help touch up appearance.	<u>CLEANUP INFORMATION</u> Clean spills, spatters, hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with compliant cleanup solvent to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using solvents.
Caulking Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with the appropriate caulk after priming the surface.	<p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative or visit www.paintdocs.com to obtain the most current version of the PDS and/or an SDS.</p>	